



Ideal Versatility, Durability and Scratch Resistance with a Seamless Design

3D Laminates are best suited for vertical applications, such as cabinet doors and boxes, drawers, drawer fronts and closet system components. As a 3D Laminate, these products can be membrane-pressed or vacuum-formed, enabling a seamless contoured design and eliminating the need for T-molding and edgebanding.

Benefits

- Contoured edges allow for harmonious design without visible lines typical of edgebanding
- Seamless design helps mitigate potential contaminants and simplifies cleaning
- Abrasion and scratch resistance provide a long-lasting, "like new" appearance
- OMNOVA offers a robust matching partnership with a variety of Thermally Fused Laminate (TFL) manufacturers, allowing you to integrate TFL designs with our 3D Laminates for a seamlessly blended finished product.
- **Echo™** 3D Emboss-in-Register technology – capturing true to nature realism in both woodgrains and stones – available in some SURTECO original designs
- SURTECO exclusive designs representing the forefront of commercial and residential interior trends
- Domestic supply
- Stock products available for immediate shipment
- Custom colors, patterns and embossings available to create differentiated products

KCMA Chemical Resistance (9.3)

| Staining Agent | Typical Test Results* |
|--------------------|-----------------------|
| Vinegar | No effect |
| Lemon Juice | No effect |
| Grape Juice | No effect |
| Orange Juice | No effect |
| Tomato Ketchup | No effect |
| Coffee | No effect |
| Olive Oil | No effect |
| Alcohol, 100 Proof | No effect |
| Detergent Solution | No effect |
| Mustard | Moderate effect |

*Results

No effect = no discoloration or stain after cleaning immediately with water.

Moderate effect = slight stain or discoloration apparent after cleaning.

Severe effect = definite stain after cleaning, remaining after 14 days.

Stock Product Information

| | |
|--------------------|-------------------------|
| Usable Film Width* | 53" (+/- 0.05") |
| Film Thickness | 10 – 20 mil |
| Roll Lengths | 50 and 250 linear yards |

*Custom widths available

Typical Properties

| Test Method | 3D Laminates |
|---------------------|-------------------|
| Hoffman Scratch | 900 – 1300 g |
| Erichsen Scratch | 4.5 – 8.0 N |
| NEMA Ball Impact | 3000 mm |
| NEMA Wear (Initial) | 900 – 1050 cycles |

The above listed values are typical and not intended as product specifications.

Care & Cleaning

The following care instructions will help maintain the lifecycle of our 3D Laminates:

- Do not expose the 3D Laminate surface to hot temperatures (temperatures exceeding ~140 °F)
- Avoid using sharp objects like knives and scissors that can damage the surface.
- Ceramics and other abrasive objects may cause scratching or marring.

Cleaning Instructions

Easy clean-up. Immediately clean spills. Acceptable household name brand cleaners include Windex® Original Glass Cleaner (S.C. Johnson), Fantastik® (S.C. Johnson) and Simple Green® (Sunshine Makers). Persistent stains can be removed using a cleaner such as Clorox® Clean-Up®. In lab settings, stains exposed to Clorox® Clean-Up® for 5 minutes were successfully wiped clean with a paper towel. Avoid abrasive cleaning agents, such as scouring pads, Comet® Cleanser, Bar Keepers Friend® or cleaners containing baking soda.

Additionally, avoid using the following when cleaning as they can soften and remove a laminate's coating:

- Ketones (methyl ethyl ketone (MEK), acetone)
- Chlorinated Hydrocarbons (methylene chloride)
- Aromatic Hydrocarbons (toluene, xylene)
- Lacquer thinners

For persistent stains, please refer to the full list of approved disinfectants found in our Laminates Chemical Resistance Technical Bulletin.

Fabrication Recommendations

Board preparation is essential to achieve the best look and feel. A well-sanded, smooth surface that is free from defects, bumps and divots minimizes the potential for telegraphing. SURTECO recommends using a double-refined or ultra-refined MDF board for best results. The use of polycrystalline diamond (PCD) tipped tooling may yield better consistency, throughput and overall economics. The tooling manufacturer can provide the optimal RPM range to use for a given tool, essential to achieve the desired cut quality.

A uniform coating of adhesive is important to prevent glue unevenness or telegraphing. Proper mixing is required if using a two-part adhesive system. Prior to applying adhesive, the board should be blown clean to ensure no dust or contaminants are sealed in by the adhesive. For edges and routed areas, SURTECO recommends two or more coats. For specific details on mixing or spraying (fan, nozzle, pressure or atomization) conditions, contact the adhesive supplier.

3D Laminates have been successfully pressed using standard membrane press operating conditions. However, each customer should complete its own independent trials to determine the optimum processing conditions to meet its needs. As with all membrane pressed parts, achieving the required activation temperature of the adhesive at the very bottom edge of the part is imperative.

Storage & Handling

3D Laminates are susceptible to heat and pressure. Extreme temperature and pressures can affect the product characteristics and performance. Due to shipping and storage variations, shelf life cannot be guaranteed. However, the following storage guidelines help to ensure optimal performance:

- Keep the product in its original packaging, partial rolls included.
- Storage conditions should maintain a temperature range of 55° to 75°F and a relative humidity of approximately 50%.
 - Product should be acclimated 48 hours prior to processing.
 - Extreme cold may cause brittleness and extreme heat may soften the film and cause shrinkage.
 - High humidity can cause moisture which can weaken the bond and possibly cause blocking within the roll.

Though SURTECO Laminates can be used in many applications, all laminates are sold with the understanding that customers will make their own independent determination whether a particular laminate has the durability and other performance attributes required for the specific end use laminate application – not all laminates are suited for all applications.

For the latest designs, more information or to place an order, contact SURTECO:
866-332-5226 • laminates@surteco.com

Revision Date: 30-Apr-21

Page 3 of 3

www.surteco.com/northamerica

SURTECO

North American Office
32125 Solon Road, Suite 150
Solon, OH 44139
United States
PHONE +1 216 682-7000
FAX +1 216 453-0104